

3M Double Coated Tissue Tape

90775

Product Description

3M™ 90775 is a tissue tape with both side with a high adhesion acrylic pressure sensitive adhesive. This tape is protected by a polycoated white paper release liner with blue 3M logo printed.

It features dimensional stability and improved handling with ease of die cutting and laminating because of non-woven with high tensile strength. 3M™ High Performance Acrylic Adhesive provides high bond strength on many kinds of surfaces.

Feature

- 90775 provides excellent initial tack and adhesion to a wide variety surface including many low surface energy plastics.
- This tape has a non-woven carrier which can add dimensional stability and also makes it easier to handle the tape during punching use and die-cutting.

Application Idea

- General purpose joining and mounting application at indoor and outdoor use
- Holding and bonding of electronic parts
- Electronic Components Bonding / Attachments
- Appliance parts attachments

Construction

Product	90775
Adhesive Type	High Performance Acrylic adhesive
Tape Thickness	0.08 mm(± 15%)
Tape Color	Off-White
Carrier	Tissue
Release Liner	Silicone treated Poly Coated Kraft (Blue 3M logo printed)



Liner Thickness	0.135mm (± 10%)
Roll Size	1200mm wide 50M, 100M

3M Double Coated Tissue Tape

90775

page 2 of 3

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product	90775	
180 ° Peel Strength	<u>kg/in</u>	
ASTM D-3330		
Initial		
SS	1.0	
PC	1.0	
PP	0.6	
RT 72hr		
SS	1.1	
PC	1.3	
PP	0.7	
Tensile & Elongation		
ASTM D-3822		
D-5035	<u>MD</u>	<u>CD</u>
Tensile (kg/in)	4.0	0.8
Elongation (%)	5	2
Shear Strength		
ASTM D-3654 modified – (1 inch ²) on SUS		
1000gram at RT (23 ± 2°C)	>10,000min	
Relative High Temperature Operating Ranges :		
Long Term(days, weeks)	195°F(90°C)	
Short Term(minutes, hours)	250°F(120°C)	
Release Level	25 g/in	
ASTM D-3330		
Shelf Life	12months from date of manufacture when stored in original cartons at room temperature & 50% RH	

3M Double Coated Tissue Tape

90775

page 3 of 3

Application Technique

- Bond strength is dependent upon the amount of adhesive to surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength.
- To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Typical surface cleaning solvents are isopropyl alcohol and water (rubbing alcohol) or heptane.

Note : Be sure to follow manufacturer's safety precautions and directions for use when using solvents.

- Ideal tape application temperature range is 70°F To 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

For Additional Information

To request additional product information or to arrange for sales assistance, call 82-2-3771-4097. Address correspondence to : 3M Industrial Adhesive & Tapes Division, 3M Korea LTD, Hana Daetoo Securities BLDG 22nd Floor, Yoido Dong, Yongdeungpogu, Seoul, Korea. Our fax number is 82-2-786-7429

Important Notice

3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. Please remember that many factors can affect the use and performance of a 3M IATD product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M IATD product. Given the variety of factors that can affect the use and performance of a 3M IATD product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M IATD product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Limitation of Remedies and Liability

If the 3M product is provided to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the theory asserted, including negligence, warranty, or strict liability.

ISO 9002

This Tape & Adhesives Organization product was manufactured under a 3M quality system registered to ISO 9002 standards.



Industrial Adhesives & Tapes Division

3M Korea LTD, Hana Daetoo Securities BLDG 19th,
Yoido-Dong, Yongdeungpo-Gu,
Seoul, Korea
82-2-3771-4097
www.3M.com

Copyright © 2010